

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 06-220145

(43)Date of publication of application : 09.08.1994

(51)Int.Cl.

C08F299/02
C08F 2/44
C08L 33/00
// B29C 43/20
B29K101:10
B29K105:06

(21)Application number : 05-013275

(71)Applicant : SEKISUI CHEM CO LTD

(22)Date of filing : 29.01.1993

(72)Inventor : MORISHITA NATSUKI

(54) RESIN COMPOSITION FOR COATING IN MOLD

(57)Abstract:

PURPOSE: To provide a thermoplastic resin composition for coating in a mold, capable of forming irregular color-free and uniformly colored coating layers on thermosetting molding materials.

CONSTITUTION: At least one of the combinations from among (1) a polyamine or unsaturated amine and a carboxyl group-containing resin, (2) the polyamine or unsaturated amine and a polycarboxylic acid, (3) the polyamine and an unsaturated carboxylic acid, and (4) an alkaline earth metal element or zinc oxide or hydroxide and the carboxyl group-containing resin is added to a thermosetting resin composition for coating in a mold to provide the resin composition thickened into a viscosity of 150-550 poises (25°C).

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's
decision of rejection]

[Date of requesting appeal against examiner's
decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2000 Japan Patent Office